
**EFFECTS OF GRINDING PARAMETERS ON SURFACE ROUGHNESS
WHEN EXTERNAL CYLINDRICAL GRINDING SKD11 STEEL USING
HAI DUONG GRINDING WHEEL**

Vu Nhu Nguyet

Mechanical Engineering Faculty, Thai Nguyen University, 3-2 Street, Tich Luong Ward, Thai
Nguyen City

Abstract

This paper presents the effect of grinding parameters on surface roughness when external cylindrical grinding SKD11 steel using Hai Duong grinding wheel. Three grinding parameters mentioned in this study include workpiece velocity, depth of cut, and longitudinal feed rate. The factor selected as the criterion for evaluating the grinding process is the surface roughness of the workpiece. The Hai Duong grinding wheel, Cn80.G.V1,400x50x207x35m/s, was used in this study. The experiment was conducted with 15 experiments according to the Box-Behken matrix. After analyzing experimental results, the three grinding parameters significantly affected surface roughness. The influence of the interaction between the grinding parameters on surface roughness was also analyzed in this study. This study has also built a regression model on the relationship between surface roughness and the grinding parameters with the correlation coefficient 96.69%. This is the basis for selecting and controlling the value of the grinding parameters in order to obtain the surface roughness according to specific requirements. Finally, the further research is also mentioned in this paper.

Keywords: SKD11 steel, external cylindrical grinding, Hai Duong grinding wheel, grinding parameters, surface roughness.

1. Introduction

In machining process, external cylindrical grinding is commonly used to refine important surfaces [1, 2]. Surface quality of external cylindrical grinding is evaluated by many parameters. In particular, surface roughness is a factor that greatly influences the working ability of elements and is often used as a criterion for evaluating the quality of grinding materials [1, 2].

SKD11 steel is widely used to manufacture moulds and cutting tools with the outstanding advantages such as high hardness, high abrasion resistance, low quenching stress [3]. The research on grinding SKD11 steel has been conducted by a number of researches such as study on cutting force, surface roughness and chip thickness when using minimum quantity lubrication (MQL) technology [5], the influence of cutting parameters on surface roughness when grinding with CBN grinding wheel [6, 7], the effect of cutting parameters on cutting force when grinding with discontinuous grinding wheel [4], evaluating the cutting ability of CBN grinding by electroplating method in Vietnam [9], and the influence of cutting parameters on surface roughness when grinding with CBN wheel [8].

Hai Duong grinding wheel manufactured by Hai Duong Grinding Company in Vietnam is a commonly used in the machining process. In addition, this grinding wheel is also being exported

to countries such as Serilanka, Indonesia, and Korea with large annual output. However, there has not mentioned any researches investigating the effect of grinding parameters on surface roughness when external cylindrical grinding SKD11 steel by Hai Duong grinding wheel.

In this paper, the experimental method is used to determine the effect of grinding parameters on surface roughness when external cylindrical grinding SKD11 steel using Hai Duong grinding wheel.

2. Experiment system

- Machine: using external cylindrical machine TOYODA 45M in Thai Nguyen University of Technology.



Fig. 1. Grinding machine

- Hai Duong grinding wheel: Cn100.G. TB₁. V₁.400x50x207x35m/s.

- Experimental material is SKD11 steel. Before the experiment, the workpiece was machined through turning steps, heat treatment reached hardness 62HRC, semi-sharp grinding, and the diameter of workpiece Ø30. The chemical composition of SKD11 steel after heat treatment is shown in Table 1.

Table 1. Chemical composition of SKD11 steel

| Chemical element | C | Mn | Si | Cr | V | Mo | Ni |
|------------------|------|------|------|------|------|------|------|
| % | 1,56 | 0,32 | 0,22 | 11,5 | 0,21 | 0,36 | 0,32 |

- Roughness measurement device is SJ201 Mitutoyo, Japan as shown in Fig. 1.



Hình 2. Roughness measurement device SJ201

- Soluble oil: emusil 5% with flood cooling method and flow 40 liters/min.
- Dresser: multipoint, symbol 3908-0088C.

3. Experimental design

The experiment was conducted according to the Box-Behnken matrix, which is commonly used in experimental optimization [10]. The value of the input parameters is suitably selected for fine grinding conditions of high hardness materials and suitable for technological capabilities of machines. Values at the three levels of the grinding parameters for experiments are shown in Table 2.

Table 2. Grinding parameters and their values at the three levels

| Grinding parameters | Symbol | Unit | Level | | |
|------------------------|--------|--------|-------|------|------|
| | | | -1 | 0 | 1 |
| Workpiece velocity | v | m/min | 22 | 26 | 30 |
| Depth of cut | t | mm | 0.01 | 0.02 | 0.03 |
| Longitudinal feed rate | f | mm/rev | 4 | 6 | 8 |

Experimental matrix of Box-Behnken for 3 experimental variables (v , t , f) at the three levels of grinding parameters was designed by Minitab 16 software as shown in Table 3.

Table 3. Experiment matrix

| No. | Levels | | |
|-----|----------|----------|----------|
| | <i>v</i> | <i>t</i> | <i>f</i> |
| 1 | -1 | -1 | 0 |
| 2 | 1 | -1 | 0 |
| 3 | -1 | 1 | 0 |
| 4 | 1 | 1 | 0 |
| 5 | -1 | 0 | -1 |
| 6 | 1 | 0 | -1 |
| 7 | -1 | 0 | 1 |
| 8 | 1 | 0 | 1 |
| 9 | 0 | -1 | -1 |
| 10 | 0 | 1 | -1 |
| 11 | 0 | -1 | 1 |
| 12 | 0 | 1 | 1 |
| 13 | 0 | 0 | 0 |
| 14 | 0 | 0 | 0 |
| 15 | 0 | 0 | 0 |

4. Result and discussion

The experiment was carried out for SKD11 steel grinding test with 15 test runs as shown in Table 3. At each test run, grinding samples are performed on three samples, with each sample measuring the roughness at least 3 times. The roughness value at each experimental point is presented in Table 4.

Table 4. Results of the experiment

| Test run No. | Grinding parameters | | | | | | Ra (µm) |
|--------------|---------------------|----|----|-----------|--------|------------|---------|
| | Level | | | Value | | | |
| | v | t | f | v (m/min) | t (mm) | f (mm/rev) | |
| 1 | -1 | -1 | 0 | 22 | 0.01 | 6 | 0.83 |
| 2 | 1 | -1 | 0 | 30 | 0.01 | 6 | 0.90 |
| 3 | -1 | 1 | 0 | 22 | 0.03 | 6 | 1.55 |
| 4 | 1 | 1 | 0 | 30 | 0.03 | 6 | 2.56 |
| 5 | -1 | 0 | -1 | 22 | 0.02 | 4 | 1.66 |
| 6 | 1 | 0 | -1 | 30 | 0.02 | 4 | 1.48 |
| 7 | -1 | 0 | 1 | 22 | 0.02 | 8 | 1.68 |
| 8 | 1 | 0 | 1 | 30 | 0.02 | 8 | 2.96 |
| 9 | 0 | -1 | -1 | 26 | 0.01 | 4 | 1.13 |
| 10 | 0 | 1 | -1 | 26 | 0.03 | 4 | 1.01 |
| 11 | 0 | -1 | 1 | 26 | 0.01 | 8 | 1.59 |
| 12 | 0 | 1 | 1 | 26 | 0.03 | 8 | 3.09 |
| 13 | 0 | 0 | 0 | 26 | 0.02 | 6 | 0.96 |
| 14 | 0 | 0 | 0 | 26 | 0.02 | 6 | 0.98 |
| 15 | 0 | 0 | 0 | 26 | 0.02 | 6 | 0.90 |

The ANOVA analysis results for surface roughness are presented as in Table 5.

Table 5. Results of ANOVA analysis

| | <i>df</i> | <i>SS</i> | <i>MS</i> | <i>F</i> | <i>Significance F</i> | | | |
|------------|---------------------|-----------------------|---------------|----------------|-----------------------|------------------|--------------------|--------------------|
| Regression | 9 | 7.6559 | 0.8507 | 16.2364 | 0.0034 | | | |
| Residual | 5 | 0.2620 | 0.0524 | | | | | |
| Total | 14 | 7.9178 | | | | | | |
| | <i>Coefficients</i> | <i>Standard Error</i> | <i>t Stat</i> | <i>P-value</i> | <i>Lower 95%</i> | <i>Upper 95%</i> | <i>Lower 95.0%</i> | <i>Upper 95.0%</i> |
| Intercept | 0.9467 | 0.1322 | 7.1635 | 0.0008 | 0.6070 | 1.2864 | 0.6070 | 1.2864 |
| v | 0.2733 | 0.0809 | 3.3770 | 0.0197 | 0.0653 | 0.4813 | 0.0653 | 0.4813 |
| t | 0.4689 | 0.0809 | 5.7943 | 0.0022 | 0.2609 | 0.6769 | 0.2609 | 0.6769 |
| f | 0.5053 | 0.0809 | 6.2446 | 0.0015 | 0.2973 | 0.7134 | 0.2973 | 0.7134 |
| v * v | 0.3786 | 0.1191 | 3.1781 | 0.0246 | 0.0724 | 0.6848 | 0.0724 | 0.6848 |
| t * t | 0.1376 | 0.1191 | 1.1548 | 0.3004 | -0.1686 | 0.4438 | -0.1686 | 0.4438 |
| f * f | 0.6209 | 0.1191 | 5.2120 | 0.0034 | 0.3146 | 0.9271 | 0.3146 | 0.9271 |
| v * t | 0.2363 | 0.1144 | 2.0644 | 0.0939 | -0.0579 | 0.5305 | -0.0579 | 0.5305 |
| v * f | 0.3659 | 0.1144 | 3.1975 | 0.0241 | 0.0718 | 0.6601 | 0.0718 | 0.6601 |
| t * f | 0.4035 | 0.1144 | 3.5260 | 0.0168 | 0.1093 | 0.6977 | 0.1093 | 0.6977 |

The results in Table 4 show that:

- All three parameters such as the workpiece velocity, depth of cut and longitudinal feed rate have a significant influence on the surface roughness as shown in Fig. 2. The value of workpiece velocity increases from 22 m/ min to 26 m/ min, the roughness of the surface is less changed. However, when the workpiece velocity increases from 26 m / min or more, the surface roughness increases rapidly. For the depth of cut, increasing the value of depth of cut will cause to rapidly increase the surface roughness. When the longitudinal feed rate increases from 4 mm/ stroke to 6 mm/ stroke, the roughness of the surface is little changed, however, if the value of longitudinal feed rate is 6mm/ stroke or higher, the surface roughness increases very quickly.

- Regarding to the interaction effect between parameters, the interaction between the depth of cut and the longitudinal feed rate has the greatest impact on surface roughness. The following effect is the interaction between the workpiece velocity and the longitudinal feed rate. The interaction between the workpiece velocity and the depth of cut has little effect on surface roughness. To verify the results, it can be seen in Fig. 3.




Fig 3. The effect of the grinding parameters on surface roughness




Fig 4. The effect of interaction between the parameters on surface roughness

As shown in Table 5, the relationship between surface roughness and grinding parameters is expressed in the regression equations (1). From this equation, it can be easy to determine the surface roughness depending values of input parameters. This equation has a correlation coefficient $R^2 = 0.9669$. This coefficient is very close to 1, which proves that equation (1) has a great match compared to experimental data. This can be used to predict surface roughness. The results were compared with experimental values as shown in Table 4 and Fig 4.

$$Ra = 0.9467 + 0.2733*v + 0.4689*t + 0.5053*f + 0.3786 v^2 + 0.1376*t^2 + 0.6209*f^2 + 0.2363* v*t + 0.3659*v*f + 0.4035*t*f \quad (1)$$




Fig. 5. Comparison between the theory as shown in Eq. (1) and the experiment

The observation in Fig 4 shows that the surface roughness according to equation (1) is very close to the experimental values. The average deviation between the predicted results and the experimental results is only about 8.21%. From that, the regression model presented in (1) is completely suitable for predicting surface roughness when external cylindrical grinding SKD11 steel by using grinding wheel Cn80.G.V1.400x50x207x35m/s.

5. Conclusion

This paper proposed the effect of grinding parameters on surface roughness when external cylindrical grinding SKD11 steel using Hai Duong grinding wheel. Some conclusions are drawn as follows:

- The process of experiment for grinding SKD11 steel by using Hai Duong grinding wheel was done in order to determine the influence of grinding parameters including workpiece velocity, depth of cut and longitudinal feed rate on surface roughness of workpiece. The effect of the interaction between these parameters on surface roughness was also performed. This study has also built the model to predict the surface roughness depending on grinding parameters. This is the basis for selecting the suitable value of the grinding parameters to ensure the value of surface roughness in each specific case.
- The influence of the dressing parameters, cooling and lubrication technology on surface roughness has not been mentioned; thus determining the optimal value of these parameters for grinding process will be discussed in further studies.

Acknowledgement

The work was supported by Thai Nguyen University of Technology for a scientific project (<http://tnut.edu.vn/>).

References

- [1]. Marinescu Loan D., Eckart Uhlmann and Brian Rowe W., (2006), *Handbook of machining with grinding wheels*, CRC Press Taylor & Francis Group.
- [2]. Stephen Malkin, Changsheng Guo, (2008), *Grinding technology - theory and applications of machining with abrasives – Second editor*, Industrial Press, New York, 2008.
- [3]. Ashton Acton Q., (2012), *Advances in Nanotechnology Research and Application*, Scholarly Editions, Atlanta, Georgia.
- [4]. Bobby O. P. Soepangkat, H. C. Kis Agustin, and H. Subiyanto, (2017), *An investigation of force, surface roughness and chip in surface grinding of SKD 11 tool steel using minimum quantity lubrication-MQL technique*, American Institute of Physics, pp.1-7.
- [5]. Ming WW, Liu G, Chen M, (2007), *Experimental study on the hardened surface layer of grinding SKD-11 hardened steel*, Key Eng Mater 359–360:224–228.
- [6]. Ming WW, Liu G, Chen M (2007), *Study on surface grind-hardening of SKD-11 hardened steel*. Int J Manuf Tech Manag 12(1/2/3), pp.236-242.
- [7]. Nguyen Thi Phuong, Nguyen Thi Phuong Giang, Nguyen Tien Dong, (2017), *A research on the effect of cutting parameters on cutting force in flat grinding using segmented grinding wheel*, Vietnam Journal of Science and Technology 55 (6), pp. 793-802.
- [8]. Tran Thi Van Nga, (2017), *Research on fabrication and assessment cutting ability of electroplated metal-bonded CBN grinding wheel*, PhD thesis, National Research Institute of Mechanical Engineering – Ministry of Industry and Trade (in Vietnamese).
- [9]. Chih Hsiang Chang, Jhy Cherng Tsai, Neng Hsin Chiu, Rei Yu Chein, (2010), *Modeling Surface Roughness and Hardness of Grinding SKD11 Steel Using Adaptive Network Based Fuzzy Inference*, Advanced Materials Research, vol. 126, pp. 171-176.
- [10]. Nguyen Van Du, Nguyen Dang Binh (2011), *Design of experiment techniques*, Science and technics publishing House (in Vietnamese).